



TEST REPORT

Applicant: Dezhou Jiasheng Rubber and Plastic Products Co., LTD
Address: Workshop 2, Yard 1397, Baide Road, Songguantun Sub-district Office, Dezhou Economic and Technological Development Zone, Shandong Province





Manufacturer: Dezhou Jiasheng Rubber and Plastic Products Co., LTD
Address: Workshop 2, Yard 1397, Baide Road, Songguantun Sub-district Office, Dezhou Economic and Technological Development Zone, Shandong Province

The following samples were submitted and identified on behalf of the clients as:

Sample name: Ultra MW polyethylene board/ UHWM-PE board
Brand: N/A
Model(s): N/A
Batch No.: N/A
Sample received date: May 12, 2022
Testing period: May 12, 2022 to May 23, 2022
Test Method: Please refer to next page(s).
Test Result: Please refer to next page(s).

Result Summary :

Test Requested	Conclusion
US FDA 21 CFR 177.1520, Olefin polymers	PASS

Tested By: 	Check By: 	Approve By:  
--	---	--

Date: May 23, 2022

Note: If there is any objection to the inspection results in this report, please submit a written report to the company within 15 days from the date of receiving the report. The test report is effective only with both signature and specialized stamp. This result(s) shown in this report refer only to the sample(s) tested. Without written approval of Shenzhen CTB Testing Technology Co., Ltd. this report can't be reproduced except in full. The tested sample(s) and the sample information are provided by the client. "*" indicates the testing items were fulfilled by subcontracted lab. "#" indicates the items are not in CNAS accreditation scope.



TEST REPORT

Page 2 of 4

REPORT No. : CTB220513031CX

Sample Description:

No.	Description
1	Blue plastic board

Shenzhen CTB Testing Technology Co., Ltd.

Add: Floor 1&2, Building A, No. 26 of Xinhe Road, Xinqiao Street, Baoan District, Shenzhen, China

Tel: 4008-707-283 Web: <http://www.ctb-lab.net>

Email: ctb@ctb-lab.net



TEST REPORT

Page 3 of 4

REPORT No. : CTB220513031CX

FDA 21 CFR 177.1520

For Polyethylene for use in articles that contact food except for articles used for packing or holding food during cooking:

Test item	Specification	MDL	Unit	Results
				1
Density	0.85-1.00	--	g/cm ³	0.90
Extractable fraction in N-hexane at 50 °C	Maximum 5.5	1.0	%	N.D
Soluble fraction in xylene at 25 °C	Maximum 11.30	0.5	%	N.D
Conclusion	--	--	--	PASS

Note:

1. g/cm³ = gram per cubic centimeter
2. % = percentage
3. °C = degrees Centigrade
4. N.D = Not detected (less than MDL)
5. MDL = Method detection limit



Shenzhen CTB Testing Technology Co., Ltd.

Add: Floor 1&2, Building A, No. 26 of Xinhe Road, Xinqiao Street, Baoan District, Shenzhen, China

Tel: 4008-707-283 Web: <http://www.ctb-lab.net>

Email: ctb@ctb-lab.net

Photo documentation



*** End of Report ***